

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of Claims in this application. Claims 1-18, 21, and 26-29 are currently amended. New Claim 58 is presented.


Listing of Claims

1. (currently amended) A catalyst composition comprising the contact product of at least one a first metallocene compound, at least one a second metallocene compound, at least one chemically-treated solid oxide, and at least one organoaluminum compound, wherein:

a) the at least one first metallocene compound is selected from an *ansa*-metallocene having the following formula:



wherein (X^1) and (X^2) are jointly selected from a fluorenyl and a cyclopentadienyl, a fluorenyl and an indenyl, or two fluorenyls, any one of which can be substituted, unsubstituted, partially saturated, or any combination thereof;
or



wherein (X^1) and (X^2) are jointly selected from two indenyls, any one of which can be substituted, unsubstituted, partially saturated, or any combination thereof;

wherein M^1 is selected from Ti, Zr, or Hf;

wherein (X^1) and (X^2) are connected by a substituted or unsubstituted bridging group comprising:


i) one atom selected from carbon, silicon, germanium, or tin, bonded to both (X^1) and (X^2) ; or

ii) two contiguous carbon atoms in a chain, one end of which is bonded to (X^1) and the other end of which is bonded to (X^2) ; and

wherein (X^3) ; (X^4) ; each substituent on the substituted cyclopentadienyl, the substituted indenyl, and the substituted fluorenyl; and each substituent on the substituted bridging group is independently selected from a hydrocarbyl group, an aliphatic group, an aromatic group, a cyclic

group, a combination of aliphatic and cyclic groups, an oxygen group, a sulfur group, a nitrogen group, a phosphorus group, an arsenic group, a carbon group, a silicon group, a germanium group, a tin group, a lead group, a boron group, an aluminum group, ~~an inorganic group, an organometallic group,~~ $-\text{SO}_2\text{X}$, $-\text{OAlX}_2$, $-\text{OSiX}_3$, $-\text{OPX}_2$, $-\text{SX}$, $-\text{OSO}_2\text{X}$, $-\text{AsX}_2$, $-\text{As}(\text{O})\text{X}_2$, or $-\text{PX}_2$, wherein X is selected independently from halide, H, NH_2 , OR, or SR, wherein R is a hydrocarbyl, or a substituted derivative thereof, any of which having from 1 to about 20 carbon atoms; a halide; or hydrogen;

b) the at least one second metallocene compound is an *ansa*-metallocene having the following formula:



wherein M^2 is selected from Ti, Zr, or Hf;

wherein (X^5) and (X^6) are respectively ~~independently selected from a cyclopentadienyl or a substituted cyclopentadienyl;~~

wherein (X^5) and (X^6) are connected by a substituted or unsubstituted bridging group comprising:

- i) one atom selected from carbon, silicon, germanium, or tin, bonded to both (X^5) and (X^6) ; or
- ii) two contiguous carbon atoms in a chain, one end of which is bonded to (X^5) and the other end of which is bonded to (X^6) ; and


wherein ~~when (X^5) and (X^6) is a substituted cyclopentadienyl, the substituted cyclopentadienyl is~~ are each optionally substituted with up to four substituents[$[\text{,}]$] in addition to the bridging group;

wherein (X^7) ; (X^8) ; each substituent on the substituted cyclopentadienyl; and each substituent on the substituted bridging group is independently selected from a hydrocarbyl group, an aliphatic group, an aromatic group, a cyclic group, a combination of aliphatic and cyclic groups, an oxygen group, a sulfur group, a nitrogen group, a phosphorus group, an arsenic group, a carbon group, a silicon group, a germanium group, a tin group, a lead group, a boron group, an aluminum group, ~~an inorganic group, an organometallic group,~~ $-\text{SO}_2\text{X}$, $-\text{OAlX}_2$, $-\text{OSiX}_3$, $-\text{OPX}_2$, $-\text{SX}$, $-\text{OSO}_2\text{X}$, $-\text{AsX}_2$, $-\text{As}(\text{O})\text{X}_2$, or $-\text{PX}_2$, wherein X is selected independently from halide, H,

NH₂, OR, or SR, wherein R is a hydrocarbyl, or a substituted derivative thereof, any of which
having from 1 to about 20 carbon atoms; a halide; or hydrogen; and

c) the at least one chemically-treated solid oxide comprises a solid oxide treated with an electron-withdrawing anion.

2. (currently amended) The catalyst composition of Claim 1, wherein the at least one organoaluminum compound has the following formula:



wherein (X⁹) is a hydrocarbyl having from 1 to about 20 carbon atoms; (X¹⁰) is selected from alkoxide or aryloxy having from 1 to about 20 carbon atoms, halide, or hydride; and n is a number from 1 to 3, inclusive.


3. (currently amended) The catalyst composition of Claim 1, ~~wherein the chemically-treated solid oxide comprises a solid oxide treated with an electron-withdrawing anion, wherein:~~

the solid oxide is selected from silica, alumina, silica-alumina, aluminum phosphate, heteropolytungstates, titania, zirconia, magnesia, boria, zinc oxide, mixed oxides thereof, or mixtures thereof; and


the electron-withdrawing anion is selected from fluoride, chloride, bromide, phosphate, triflate, bisulfate, sulfate, or any combination thereof.

4. (currently amended) The catalyst composition of Claim 1, wherein:

a) the at least one first metallocene compound is selected from an *ansa*-metallocene having the following formula:



wherein (X¹) and (X²) are jointly selected from a fluorenyl and a cyclopentadienyl, a fluorenyl and an indenyl, or two fluorenyls, any one of which can be substituted, unsubstituted, partially saturated, or any combination thereof;
or



wherein (X¹) and (X²) are jointly selected from two indenyls, any one of which can be substituted, unsubstituted, partially saturated, or any combination thereof;


wherein M¹ is selected from Zr or Hf;

wherein (X¹) and (X²) are connected by a bridging group selected from >CR¹₂, >SiR¹₂, or -CR¹₂CR¹₂-, wherein R¹ in each instance is independently selected from a linear, branched, substituted, or unsubstituted hydrocarbyl group, any one of which having from 1 to about 20 carbon atoms; or hydrogen;

wherein any substituent on (X¹), (X²), or R¹ is independently selected from a hydrocarbyl group, an oxygen group, a sulfur group, a nitrogen group, or a phosphorus group, ~~an inorganic group, an organometallic group,~~ any of which having from 1 to about 20 carbon atoms; a halide; or hydrogen; and

wherein (X³) and (X⁴) are independently selected from alkoxide or aryloxy having from 1 to about 20 carbon atoms, halide, or hydride; and

b) the at least one second metallocene compound is an *ansa*-metallocene having the following formula:



wherein (X⁵) and (X⁶) are respectively ~~independently selected from a cyclopentadienyl or a substituted cyclopentadienyl;~~


wherein (X⁵) and (X⁶) are connected by a bridging group selected from >CR²₂, >SiR²₂, or -CR²₂CR²₂-, wherein R² in each instance is independently selected from a linear, branched, substituted, or unsubstituted hydrocarbyl group, any one of which having from 1 to about 20 carbon atoms; or hydrogen;

wherein ~~when (X⁵) and (X⁶) is a substituted cyclopentadienyl, the substituted cyclopentadienyl is~~ are each optionally substituted with up to four substituents[[],] in addition to the bridging group;

wherein any substituent on (X⁵), (X⁶), or R² is independently selected from a hydrocarbyl group, an oxygen group, a sulfur group, a nitrogen group, or a phosphorus group, ~~an inorganic group, an organometallic group,~~ any of which having from 1 to about 20 carbon atoms; a halide; or hydrogen; and

wherein (X⁷) and (X⁸) are independently selected from alkoxide, aryloxy, or amide having from 1 to about 20 carbon atoms, halide, or hydride.

5. (currently amended) The catalyst composition of Claim 1, wherein the at least one first metallocene compound is an *ansa*-metallocene having the following formula:



wherein M¹ is selected from Zr or Hf;


wherein (X¹) and (X²) are jointly selected from a fluorenyl and a cyclopentadienyl or two fluorenyls, any one of which can be substituted or unsubstituted;

wherein (X¹) and (X²) are connected by a bridging group selected from >CR¹₂, >SiR¹₂, or -CR¹₂CR¹₂-, wherein R¹ in each instance is independently selected from a linear, branched, substituted, or unsubstituted hydrocarbyl group, any one of which having from 1 to about 20 carbon atoms; halide; or hydrogen;

wherein any substituent on (X¹), (X²), or R¹ is independently selected from a hydrocarbyl group, an oxygen group, a sulfur group, a nitrogen group, any one of which having from 1 to about 20 carbon atoms; or hydrogen; and

wherein (X³) and (X⁴) are independently selected from alkoxide or aryloxy having from 1 to about 20 carbon atoms, halide, or hydride.

6. (currently amended) The catalyst composition of Claim 1, wherein the at least one first metallocene compound is an *ansa*-metallocene having the following formula:




wherein (X¹) and (X²) are jointly selected from two indenyls, any one of which can be substituted or unsubstituted;

wherein (X¹) and (X²) are connected by a bridging group selected from >CR¹₂, >SiR¹₂, or -CR¹₂CR¹₂-, wherein R¹ in each instance is independently selected from a linear, branched, substituted, or unsubstituted hydrocarbyl group, any one of which having from 1 to about 20 carbon atoms; or hydrogen;

wherein any substituent on (X^1), (X^2), or R^1 is independently selected from a hydrocarbyl group, an oxygen group, a sulfur group, a nitrogen group, any one of which having from 1 to about 20 carbon atoms; or hydrogen; and


wherein (X^3) and (X^4) are independently selected from alkoxide or aryloxy having from 1 to about 20 carbon atoms, halide, or hydride.

7. (currently amended) The catalyst composition of Claim 1, wherein the at least one first metallocene compound is selected from a compound of the following formula:



wherein E is selected from C, Si, Ge, or Sn; and wherein R^1 , R^2 , and R^3 , in each instance, is independently selected from H or a hydrocarbyl group having from 1 to about 20 carbon atoms.

8. (currently amended) The catalyst composition of Claim 1, wherein the at least one first metallocene compound is selected from:



combination thereof.

9. (currently amended) The catalyst composition of Claim 1, wherein the at least one first metallocene compound is selected from:

2-(η^5 -cyclopentadienyl)-2-(η^5 -fluoren-9-yl)hex-5-ene zirconium(IV) dichloride, $[(\eta^5\text{-C}_5\text{H}_4)\text{CCH}_3(\text{CH}_2\text{CH}_2\text{CH}=\text{CH}_2)(\eta^5\text{-9-C}_{13}\text{H}_9)]\text{ZrCl}_2$;

2-(η^5 -cyclopentadienyl)-2-(η^5 -2,7-di-*tert*-butylfluoren-9-yl)hex-5-ene zirconium(IV) dichloride, $[(\eta^5\text{-C}_5\text{H}_4)\text{CCH}_3(\text{CH}_2\text{CH}_2\text{CH}=\text{CH}_2)(\eta^5\text{-9-C}_{13}\text{H}_7\text{-2,7-}^t\text{Bu}_2)]\text{ZrCl}_2$;

2-(η^5 -cyclopentadienyl)-2-(η^5 -fluoren-9-yl)hept-6-ene zirconium(IV) dichloride, $[(\eta^5\text{-C}_5\text{H}_4)\text{CCH}_3(\text{CH}_2\text{CH}_2\text{CH}_2\text{CH}=\text{CH}_2)(\eta^5\text{-9-C}_{13}\text{H}_9)]\text{ZrCl}_2$;

2-(η^5 -cyclopentadienyl)-2-(η^5 -2,7-di-*tert*-butylfluoren-9-yl)hept-6-ene zirconium(IV) dichloride, $[(\eta^5\text{-C}_5\text{H}_4)\text{CCH}_3(\text{CH}_2\text{CH}_2\text{CH}_2\text{CH}=\text{CH}_2)(\eta^5\text{-9-C}_{13}\text{H}_7\text{-2,7-}^t\text{Bu}_2)]\text{ZrCl}_2$;

1-(η^5 -cyclopentadienyl)-1-(η^5 -fluoren-9-yl)-1-phenylpent-4-ene zirconium(IV) dichloride, $[(\eta^5\text{-C}_5\text{H}_4)\text{C}(\text{C}_6\text{H}_5)(\text{CH}_2\text{CH}_2\text{CH}=\text{CH}_2)(\eta^5\text{-9-C}_{13}\text{H}_9)]\text{ZrCl}_2$;


1-(η^5 -cyclopentadienyl)-1-(η^5 -2,7-di-*tert*-butyl fluoren-9-yl)-1-phenylpent-4-ene zirconium(IV) dichloride, $[(\eta^5\text{-C}_5\text{H}_4)\text{C}(\text{C}_6\text{H}_5)(\text{CH}_2\text{CH}_2\text{CH}=\text{CH}_2)(\eta^5\text{-9-C}_{13}\text{H}_7\text{-2,7-}^t\text{Bu}_2)]\text{ZrCl}_2$;

1-(η^5 -cyclopentadienyl)-1-(η^5 -fluoren-9-yl)-1-phenylhex-5-ene zirconium(IV) dichloride, $[(\eta^5\text{-C}_5\text{H}_4)\text{C}(\text{C}_6\text{H}_5)(\text{CH}_2\text{CH}_2\text{CH}_2\text{CH}=\text{CH}_2)(\eta^5\text{-9-C}_{13}\text{H}_9)]\text{ZrCl}_2$;

1-(η^5 -cyclopentadienyl)-1-(η^5 -2,7-di-*tert*-butylfluoren-9-yl)-1-phenylhex-5-ene zirconium(IV) dichloride, $[(\eta^5\text{-C}_5\text{H}_4)\text{C}(\text{C}_6\text{H}_5)(\text{CH}_2\text{CH}_2\text{CH}_2\text{CH}=\text{CH}_2)(\eta^5\text{-9-C}_{13}\text{H}_7\text{-2,7-}^t\text{Bu}_2)]\text{ZrCl}_2$;

or any combination thereof.

10. (currently amended) The catalyst composition of Claim 1, wherein the at least one second metallocene compound is an *ansa*-metallocene having the following formula:



wherein (X^5) and (X^6) are respectively independently selected from a cyclopentadienyl or a substituted cyclopentadienyl;

wherein (X^5) and (X^6) are connected by a bridging group selected from $>\text{CR}^2_2$, $>\text{SiR}^2_2$, or $-\text{CR}^2_2\text{CR}^2_2-$, wherein R^2 in each instance is independently selected from a linear, branched,


substituted, or unsubstituted hydrocarbyl group, any one of which having from 1 to about 20 carbon atoms; or hydrogen;

wherein ~~when~~ (X⁵) and ~~or~~ (X⁶) ~~is a substituted cyclopentadienyl, the substituted cyclopentadienyl is~~ are each optionally substituted with up to four substituents[[,]] in addition to the bridging group;

wherein any substituent on (X⁵), (X⁶), or R² is independently selected from a hydrocarbyl group, an oxygen group, a sulfur group, a nitrogen group, any one of which having from 1 to about 20 carbon atoms; or hydrogen; and

wherein (X⁷) and (X⁸) are independently selected from alkoxide or aryloxy having from 1 to about 20 carbon atoms, halide, or hydride.


11. (currently amended) The catalyst composition of Claim 1, wherein the at least one second metallocene compound is selected from a compound of the following formula:



combination thereof;

wherein E is selected from C, Si, Ge, or Sn; and wherein R1, R2, R3, and R4, in each instance, is independently selected from H or a hydrocarbyl group having from 1 to about 20 carbon atoms.

12. (currently amended) The catalyst composition of Claim 1, wherein the at least one second metallocene compound is selected from:



thereof.

13. (currently amended) The catalyst composition of Claim 1, wherein:

a) the at least one first metallocene compound is selected from *rac*-C₂H₄(η^5 -Ind)₂ZrCl₂, *rac*-Me₂Si(η^5 -Ind)₂ZrCl₂, Me(octyl)Si(η^5 -Flu)₂ZrCl₂, *rac*-Me₂Si(η^5 -2-Me-4-PhInd)₂ZrCl₂, *rac*-C₂H₄(η^5 -2-MeInd)₂ZrCl₂, Me(Ph)Si(η^5 -Flu)₂ZrCl₂, or any combination thereof;

b) the at least one second metallocene compound is selected from *rac*-Me₂Si(η^5 -3-n-PrCp)₂ZrCl₂, Me₂Si(η^5 -Me₄Cp)₂ZrCl₂, Me₂Si(η^5 -Cp)₂ZrCl₂, or any combination thereof;

c) the at least one chemically-treated solid oxide is selected from fluorided alumina, chlorided alumina, sulfated alumina, fluorided silica-alumina, or any combination thereof; and

d) the at least one organoaluminum compound is selected from triethylaluminum or triisobutylaluminum.

14. (currently amended) The catalyst composition of Claim 1, wherein the at least one chemically-treated solid oxide is selected from fluorided alumina, chlorided alumina, bromided alumina, sulfated alumina, fluorided silica-alumina, chlorided silica-alumina, bromided silica-alumina, sulfated silica-alumina, fluorided silica-zirconia, chlorided silica-zirconia, bromided silica-zirconia, sulfated silica-zirconia, or any combination thereof.

15. (currently amended) The catalyst composition of Claim 1, wherein the at least one chemically-treated solid oxide further comprises a metal or metal ion selected from zinc, nickel, vanadium, silver, copper, gallium, tin, tungsten, molybdenum, or any combination thereof.


16. (currently amended) The catalyst composition of Claim 1, wherein the at least one chemically-treated solid oxide further comprises a metal or metal ion ~~and is selected from zinc-impregnated chlorided alumina, zinc-impregnated fluorided alumina, zinc-impregnated chlorided silica-alumina, zinc-impregnated fluorided silica-alumina, zinc-impregnated sulfated alumina, or any combination thereof.~~

17. (currently amended) The catalyst composition of Claim 1, wherein the weight ratio of the at least one organoaluminum compound to the at least one chemically-treated solid oxide is from about 10:1 to about 1:1,000.

18. (currently amended) The catalyst composition of Claim 1, wherein the at least one organoaluminum compound is selected from trimethylaluminum, triethylaluminum, tri-n-propylaluminum, diethylaluminum ethoxide, tri-n-butylaluminum, disobutylaluminum hydride, triisobutylaluminum, diethylaluminum chloride, or any combination thereof.


19. (original) The catalyst composition of Claim 1, further comprising ~~an optional~~ a cocatalyst selected from at least one aluminoxane, at least one organozinc compound, at least one organoboron compound, at least one ionizing ionic compound, or any combination thereof.

20. (original) The catalyst composition of Claim 1, further comprising ~~an optional~~ a cocatalyst selected from at least one aluminoxane compound, wherein the aluminoxane comprises
a cyclic aluminoxane having the formula:



R is a linear or branched alkyl having from 1 to 10 carbon atoms, and n is an integer from 3 to about 10;

a linear aluminoxane having the formula:



R is a linear or branched alkyl having from 1 to 10 carbon atoms, and n is an integer from 1 to about 50;


a cage aluminoxane having the formula $\text{R}_{5m+\alpha}^t \text{R}_{m-\alpha}^b \text{Al}_{4m} \text{O}_{3m}$, wherein m is 3 or 4 and α is $= n_{\text{Al}(3)} - n_{\text{O}(2)} + n_{\text{O}(4)}$; wherein $n_{\text{Al}(3)}$ is the number of three coordinate aluminum atoms, $n_{\text{O}(2)}$ is

the number of two coordinate oxygen atoms, $n_{O(4)}$ is the number of 4 coordinate oxygen atoms, R^t represents a terminal alkyl group, and R^b represents a bridging alkyl group; wherein R is a linear or branched alkyl having from 1 to 10 carbon atoms; or
any combination thereof.

21. (currently amended) The catalyst composition of Claim 20, wherein the molar ratio of the aluminum in the aluminoxane to the combined at least one first metallocene compound and at least one second metallocene compound in the catalyst composition is from about 1:10 to about 100,000:1.

22. (original) The catalyst composition of Claim 20, wherein the aluminoxane compound is selected from methylaluminoxane, ethylaluminoxane, n-propylaluminoxane, isopropylaluminoxane, n-butylaluminoxane, t-butylaluminoxane, sec-butylaluminoxane, isobutylaluminoxane, 1-pentylaluminoxane, 2-pentylaluminoxane, 3-pentylaluminoxane, isopentylaluminoxane, neopentylaluminoxane, or a combination thereof.

23. (original) The catalyst composition of Claim 1, further comprising ~~an optional~~ a cocatalyst selected from at least one organozinc compound, wherein the organozinc compound has the following formula:



wherein (X^{13}) is a hydrocarbyl having from 1 to about 20 carbon atoms; (X^{14}) is selected from a hydrocarbyl, an alkoxide or an aryloxy having from 1 to about 20 carbon atoms, halide, or hydride;

24. (original) The catalyst composition of Claim 1, further comprising ~~an optional~~ a cocatalyst selected from at least one organozinc compound, wherein the organozinc compound is selected from dimethylzinc, diethylzinc, dipropylzinc, dibutylzinc, dineopentylzinc, di(trimethylsilylmethyl)zinc, or any combination thereof.

25. (original) The catalyst composition of Claim 1, further comprising ~~an optional~~ a cocatalyst selected from at least one organoboron compound, wherein the organoboron compound is selected from tris(pentafluorophenyl)boron, tris[3,5-bis(trifluoromethyl)phenyl]boron, *N,N*-dimethylanilinium tetrakis(pentafluorophenyl)borate, triphenylcarbenium tetrakis(pentafluorophenyl)borate, lithium tetrakis(pentafluorophenyl)borate, *N,N*-dimethylanilinium tetrakis[3,5-bis(trifluoromethyl)phenyl]borate, triphenylcarbenium tetrakis[3,5-bis(trifluoromethyl)phenyl]borate, or a combination thereof.

26. (currently amended) The catalyst composition of Claim 25, wherein the molar ratio of the organoboron compound to the combined at least one first metallocene compound and at least one second metallocene compound in the catalyst composition is from about 0.1:1 to about 10:1.

27. (currently amended) The catalyst composition of Claim 1, further comprising ~~an optional~~ a cocatalyst selected from at least one ionizing ionic compound, wherein the ionizing ionic compound is selected from tri(*n*-butyl)ammonium tetrakis(*p*-tolyl)borate, tri(*n*-butyl)ammonium tetrakis(*m*-tolyl)borate, tri(*n*-butyl)ammonium tetrakis(2,4-dimethylphenyl)borate ~~tetrakis(2,4-dimethyl)borate~~, tri(*n*-butyl)ammonium tetrakis(3,5-dimethylphenyl)borate, tri(*n*-butyl)-ammonium tetrakis[3,5-bis(trifluoromethyl)phenyl]borate, tri(*n*-butyl)ammonium tetrakis(pentafluorophenyl)borate, *N,N*-dimethylanilinium tetrakis(*p*-tolyl)borate, *N,N*-dimethylanilinium tetrakis(*m*-tolyl)borate, *N,N*-dimethylanilinium tetrakis(2,4-dimethylphenyl)borate, *N,N*-dimethylanilinium tetrakis(3,5-dimethylphenyl)borate, *N,N*-dimethylanilinium tetrakis[3,5-bis(trifluoromethyl)phenyl]borate, *N,N*-dimethylanilinium tetrakis(pentafluorophenyl)borate, triphenylcarbenium tetrakis(*p*-tolyl)borate, triphenylcarbenium tetrakis(*m*-tolyl)borate, triphenylcarbenium tetrakis(2,4-dimethylphenyl)borate, triphenylcarbenium tetrakis(3,5-dimethylphenyl)borate, triphenylcarbenium tetrakis[3,5-bis(trifluoromethyl)phenyl]borate, triphenylcarbenium tetrakis(pentafluorophenyl)borate, tropylium tetrakis(*p*-tolyl)borate, tropylium tetrakis(*m*-tolyl)borate, tropylium tetrakis(2,4-dimethylphenyl)borate, tropylium tetrakis(3,5-dimethylphenyl)borate, tropylium tetrakis[3,5-bis(trifluoromethyl)phenyl]borate, tropylium tetrakis(pentafluorophenyl)borate, lithium tetrakis(pentafluorophenyl)borate, lithium

tetrakis(phenyl)borate, lithium tetrakis(p-tolyl)borate, lithium tetrakis(m-tolyl)borate, lithium tetrakis(2,4-dimethylphenyl)borate, lithium tetrakis(3,5-dimethylphenyl)borate, lithium tetrafluoroborate, sodium tetrakis(pentafluorophenyl)borate, sodium tetrakis(phenyl) borate, sodium tetrakis(p-tolyl)borate, sodium tetrakis(m-tolyl)borate, sodium tetrakis(2,4-dimethylphenyl)borate, sodium tetrakis(3,5-dimethylphenyl)borate, sodium tetrafluoroborate, potassium tetrakis(pentafluorophenyl)borate, potassium tetrakis(phenyl)borate, potassium tetrakis(p-tolyl)borate, potassium tetrakis(m-tolyl)borate, potassium tetrakis(2,4-dimethylphenyl)borate, potassium tetrakis(3,5-dimethylphenyl)borate, potassium tetrafluoroborate, tri(n-butyl)ammonium tetrakis(p-tolyl)aluminate, tri(n-butyl)ammonium tetrakis(m-tolyl)aluminate, tri(n-butyl)ammonium tetrakis(2,4-dimethylphenyl)aluminate ~~tetrakis(2,4-dimethyl)aluminate~~, tri(n-butyl)ammonium tetrakis(3,5-dimethylphenyl)aluminate, tri(n-butyl)ammonium tetrakis(pentafluorophenyl)aluminate, N,N-dimethylanilinium tetrakis(p-tolyl)aluminate, N,N-dimethylanilinium tetrakis(m-tolyl)aluminate, N,N-dimethylanilinium tetrakis(2,4-dimethylphenyl)aluminate, N,N-dimethylanilinium tetrakis(3,5-dimethylphenyl)aluminate, N,N-dimethylanilinium tetrakis (pentafluorophenyl)aluminate, triphenylcarbenium tetrakis(p-tolyl)aluminate, triphenylcarbenium tetrakis(m-tolyl)aluminate, triphenylcarbenium tetrakis(2,4-dimethylphenyl)aluminate, triphenylcarbenium tetrakis(3,5-dimethylphenyl)aluminate, triphenylcarbenium tetrakis(pentafluorophenyl)aluminate, tropylium tetrakis(p-tolyl)aluminate, tropylium tetrakis(m-tolyl)aluminate, tropylium tetrakis(2,4-dimethylphenyl)aluminate, tropylium tetrakis(3,5-dimethylphenyl)aluminate, tropylium tetrakis(pentafluorophenyl)aluminate, lithium tetrakis(pentafluorophenyl)aluminate, lithium tetrakis(phenyl)aluminate, lithium tetrakis(p-tolyl)aluminate, lithium tetrakis(m-tolyl)aluminate, lithium tetrakis(2,4-dimethylphenyl)aluminate, lithium tetrakis(3,5-dimethylphenyl)aluminate, lithium tetrafluoroaluminate, sodium tetrakis(pentafluorophenyl)aluminate, sodium tetrakis(phenyl)aluminate, sodium tetrakis(p-tolyl)aluminate, sodium tetrakis(m-tolyl)aluminate, sodium tetrakis(2,4-dimethylphenyl)aluminate, sodium tetrakis(3,5-dimethylphenyl)aluminate, sodium tetrafluoroaluminate, potassium tetrakis(pentafluorophenyl)aluminate, potassium tetrakis(phenyl)aluminate, potassium tetrakis(p-tolyl)aluminate, potassium tetrakis(m-tolyl)aluminate, potassium tetrakis(2,4-dimethylphenyl)aluminate, potassium tetrakis (3,5-dimethylphenyl)aluminate, potassium tetrafluoroaluminate, or any combination thereof.


28. (currently amended) A composition of matter comprising at least one a first metallocene compound, at least one a second metallocene compound, at least one chemically-treated solid oxide, and at least one organoaluminum compound, wherein:

a) the at least one first metallocene compound is selected from an *ansa*-metallocene having the following formula:



wherein (X^1) and (X^2) are jointly selected from a fluorenyl and a cyclopentadienyl, a fluorenyl and an indenyl, or two fluorenyls, any one of which can be substituted, unsubstituted, partially saturated, or any combination thereof;

or



wherein (X^1) and (X^2) are jointly selected from two indenyls, any one of which can be substituted, unsubstituted, partially saturated, or any combination thereof;

wherein M^1 is selected from Ti, Zr, or Hf;

wherein (X^1) and (X^2) are connected by a substituted or unsubstituted bridging group comprising:


i) one atom selected from carbon, silicon, germanium, or tin, bonded to both (X^1) and (X^2) ; or

ii) two contiguous carbon atoms in a chain, one end of which is bonded to (X^1) and the other end of which is bonded to (X^2) ; and

wherein (X^3) ; (X^4) ; each substituent on the substituted cyclopentadienyl, the substituted indenyl, and the substituted fluorenyl; and each substituent on the substituted bridging group is independently selected from a hydrocarbyl group, an aliphatic group, an aromatic group, a cyclic group, a combination of aliphatic and cyclic groups, an oxygen group, a sulfur group, a nitrogen group, a phosphorus group, an arsenic group, a carbon group, a silicon group, a germanium group, a tin group, a lead group, a boron group, an aluminum group, ~~an inorganic group, an organometallic group,~~ $-SO_2X$, $-OAlX_2$, $-OSiX_3$, $-OPX_2$, $-SX$, $-OSO_2X$, $-AsX_2$, $-As(O)X_2$, or $-PX_2$, wherein X is selected independently from halide, H, NH_2 , OR, or SR, wherein R is a

hydrocarbyl, or a substituted derivative thereof, any of which having from 1 to about 20 carbon atoms; a halide; or hydrogen;

b) the at least one second metallocene compound is an *ansa*-metallocene having the following formula:



wherein M^2 is selected from Ti, Zr, or Hf;

wherein (X^5) and (X^6) are respectively independently selected from a cyclopentadienyl or a substituted cyclopentadienyl;

wherein (X^5) and (X^6) are connected by a substituted or unsubstituted bridging group comprising:


- i) one atom selected from carbon, silicon, germanium, or tin, bonded to both (X^5) and (X^6) ; or
- ii) two contiguous carbon atoms in a chain, one end of which is bonded to (X^5) and the other end of which is bonded to (X^6) ; and

wherein ~~when (X^5) and (X^6) is a substituted cyclopentadienyl, the substituted cyclopentadienyl is~~ are each optionally substituted with up to four substituents[[,]] in addition to the bridging group;

wherein (X^7) ; (X^8) ; each substituent on the substituted cyclopentadienyl; and each substituent on the substituted bridging group is independently selected from a hydrocarbyl group, an aliphatic group, an aromatic group, a cyclic group, a combination of aliphatic and cyclic groups, an oxygen group, a sulfur group, a nitrogen group, a phosphorus group, an arsenic group, a carbon group, a silicon group, a germanium group, a tin group, a lead group, a boron group, an aluminum group, ~~an inorganic group, an organometallic group, $-SO_2X$, $-OAlX_2$, $-OSiX_3$, $-OPX_2$, $-SX$, $-OSO_2X$, $-AsX_2$, $-As(O)X_2$, or $-PX_2$~~ , wherein X is selected independently from halide, H, NH_2 , OR, or SR, wherein R is a hydrocarbyl, or a substituted derivative thereof, any of which having from 1 to about 20 carbon atoms; a halide; or hydrogen; ~~and~~

c) the at least one chemically-treated solid oxide comprises a solid oxide treated with an electron-withdrawing anion; and

d) the at least one organoaluminum compound has the following formula:



wherein (X⁹) is a hydrocarbyl having from 1 to about 20 carbon atoms; (X¹⁰) is selected from alkoxide or aryloxy having from 1 to about 20 carbon atoms, halide, or hydride; and n is a number from 1 to 3, inclusive.


29. (currently amended) A method of making a catalyst composition comprising contacting at least one a first metallocene compound, at least one a second metallocene compound, at least one chemically-treated solid oxide, and at least one organoaluminum compound, wherein:

a) the at least one first metallocene compound is selected from an *ansa*-metallocene having the following formula:



wherein (X¹) and (X²) are jointly selected from a fluorenyl and a cyclopentadienyl, a fluorenyl and an indenyl, or two fluorenyls, any one of which can be substituted, unsubstituted, partially saturated, or any combination thereof;

or



wherein (X¹) and (X²) are jointly selected from two indenyls, any one of which can be substituted, unsubstituted, partially saturated, or any combination thereof;

wherein M¹ is selected from Ti, Zr, or Hf;

wherein (X¹) and (X²) are connected by a substituted or unsubstituted bridging group comprising:


i) one atom selected from carbon, silicon, germanium, or tin, bonded to both (X¹) and (X²); or

ii) two contiguous carbon atoms in a chain, one end of which is bonded to (X¹) and the other end of which is bonded to (X²); and

wherein (X³); (X⁴); each substituent on the substituted cyclopentadienyl, the substituted indenyl, and the substituted fluorenyl; and each substituent on the substituted bridging group is independently selected from a hydrocarbyl group, an aliphatic group, an aromatic group, a cyclic group, a combination of aliphatic and cyclic groups, an oxygen group, a sulfur group, a nitrogen group, a phosphorus group, an arsenic group, a carbon group, a silicon group, a germanium

group, a tin group, a lead group, a boron group, an aluminum group, ~~an inorganic group, an organometallic group, -SO₂X, -OAlX₂, -OSiX₃, -OPX₂, -SX, -OSO₂X, -AsX₂, -As(O)X₂, or -PX₂~~, wherein X is selected independently from halide, H, NH₂, OR, or SR, wherein R is a hydrocarbyl, or a substituted derivative thereof, any of which having from 1 to about 20 carbon atoms; a halide; or hydrogen;

b) the at least one second metallocene compound is an *ansa*-metallocene having the following formula:



wherein M² is selected from Ti, Zr, or Hf;

wherein (X⁵) and (X⁶) are respectively independently selected from a cyclopentadienyl or a substituted cyclopentadienyl;

wherein (X⁵) and (X⁶) are connected by a substituted or unsubstituted bridging group comprising:


- i) one atom selected from carbon, silicon, germanium, or tin, bonded to both (X⁵) and (X⁶); or
- ii) two contiguous carbon atoms in a chain, one end of which is bonded to (X⁵) and the other end of which is bonded to (X⁶); and

wherein ~~when (X⁵) and (X⁶) is a substituted cyclopentadienyl, the substituted cyclopentadienyl is~~ are each optionally substituted with up to four substituents[[,]] in addition to the bridging group;

wherein (X⁷); (X⁸); each substituent on the substituted cyclopentadienyl; and each substituent on the substituted bridging group is independently selected from a hydrocarbyl group, an aliphatic group, an aromatic group, a cyclic group, a combination of aliphatic and cyclic groups, an oxygen group, a sulfur group, a nitrogen group, a phosphorus group, an arsenic group, a carbon group, a silicon group, a germanium group, a tin group, a lead group, a boron group, an aluminum group, ~~an inorganic group, an organometallic group, -SO₂X, -OAlX₂, -OSiX₃, -OPX₂, -SX, -OSO₂X, -AsX₂, -As(O)X₂, or -PX₂~~, wherein X is selected independently from halide, H, NH₂, OR, or SR, wherein R is a hydrocarbyl, or a substituted derivative thereof, any of which having from 1 to about 20 carbon atoms; a halide; or hydrogen; and

c) the at least one chemically-treated solid oxide comprises a solid oxide treated with an electron-withdrawing anion; and

d) the at least one organoaluminum compound has the following formula:



wherein (X^9) is a hydrocarbyl having from 1 to about 20 carbon atoms; (X^{10}) is selected from alkoxide or aryloxy having from 1 to about 20 carbon atoms, halide, or hydride; and n is a number from 1 to 3, inclusive.

30-57. (cancelled)

58. (new) The catalyst composition of Claim 16, wherein the at least one chemically-treated solid oxide is selected from zinc-impregnated chlorided alumina, zinc-impregnated fluorided alumina, zinc-impregnated chlorided silica-alumina, zinc-impregnated fluorided silica-alumina, zinc-impregnated sulfated alumina, or any combination thereof.